

## **Chemical Compatibility of Nitrile Rubber Products**

	Chemical Tested	Rating	Applies to the	Applies to these products:	
А	Aliphatic Hydrocarbons - Kerosene, Etc.	1			
В	Animal & Vegetable Oils	1			
С	Aromatic Hydrocarbons - Benzol, Toluol, Etc.	1			
D	Bleach	1			
E	Concentrated Alkali	1		The 1960s	
F	Cutting Oil	1			
G	Denatured Alcohol	1			
Н	Diesel	1	Comfort Flow	Comple	
I	Dilute Alkali	1			
J	Engine Oil	1	# 150000 \$ B		
K	Gasoline	1		-	
L	Hydraulic Fluid Silicate Ester	1		7723	
M	Hydraulic Fluid Water Glycol	1			
N	L.P. Gas, Fuel Oils	1			
0	Lubricating Oils - High Aniline	1		444	
Р	Lubricating Oils - Low Aniline Point	1	0 11 0 11		
Q	Mineral Spirits	1	Cushion Station	Dura	
R	Muriatic Acid - 30%, 20 Degrees Baume	1			
S	Phosphoric Acid	1	A CONTRACTOR OF THE PARTY OF TH		
T	Pine Cleaner	1			
U	Refrigerants, Ammonia	1			
٧	Sodium Hydroxide, Rayon Grade, 25%	1		Server, Server	
W	Sulphuric Acid - 30%	1	And the latest the same		
Χ	Transmission Fluid	1			
Υ	WD40	1	Hog Heaven	Hog	
Z	Water	1			
AA	Window Cleaner	1			
BB	Anti-Freeze	2			
CC	Brake Fluid	2			
DD	Calcium Hypochlorite - 12%	2	150		
EE	Chlorine Bleach - 12.5%	2			
FF	Hydraulic Fluid - Petroleum Base	2	60.0		
GG	Steam	2	Safaty Sarana	Tract	
НН	Butyl Alcohol	3	Safety Scrape	IIdu	
II	Isopropyl Alcohol - 99%	3			
JJ	Acetic Acid - 56%	4	1 = Little or no effect 2 = Minor to moderate effect 3 = Moderate to severe effect 4 = Not recommended		
KK	Acetone	4			
LL	Cyclohexane	4			
MM	Refrigerants, Methyl Chloride	4	4 = INOL TECOTI	micnaca	



Complete Comfort II



n



DuraComfort





Hog Heaven III





**Traction Tread** 

- = Little or no effect
- = Minor to moderate effect
- = Moderate to severe effect
- = Not recommended